

(19) World Intellectual Property  
Organization  
International Bureau



PCT

Rec'd PCT/PTO 05 APR 2005



10/530462

(10) International Publication Number  
WO 2004/033509 A1

(43) International Publication Date  
22 April 2004 (22.04.2004)

- (51) International Patent Classification<sup>7</sup>: C08F 10/06, C08L 23/10
- (21) International Application Number: PCT/US2003/031567
- (22) International Filing Date: 7 October 2003 (07.10.2003)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:  
60/416,632 7 October 2002 (07.10.2002) US  
60/491,586 31 July 2003 (31.07.2003) US
- (71) Applicant (*for all designated States except US*): DOW GLOBAL TECHNOLOGIES INC. [US/US]; Washington Street, 1790 Building, Midland, MI 48674 (US).
- (72) Inventors; and
- (75) Inventors/Applicants (*for US only*): PIERINI, Peter, E. [US/US]; 213 Rosemary Lane, Lake Jackson, TX 77566 (US). HARE, Marie, L. [US/US]; 123 Indian Warrior Trail, Lake Jackson, TX 77566 (US). BOSYNAK, Clive, P. [GB/US]; 8518 Halls Retreat Court, Sienna Point, Missouri City, TX 77549 (US).
- (81) Designated States (*national*): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, YU, ZA, ZM, ZW.
- (84) Designated States (*regional*): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:  
— with international search report
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: HIGHLY CRYSTALLINE POLYPROPYLENE WITH LOW XYLENE SOLUBLES

(57) Abstract: The invention is directed to a polypropylene resin which has a  $M_w/M_n$  of less than 5, a melt flow rate of less than 7 g/10 min., a 1% secant flexural modulus of greater than 300,000 psi and less than 2 wt.% xylene solubles.

WO 2004/033509 A1